


APPROVALS 批准					DOCUMENT TITLE 文件
DEPT 部门	NAME 名字	TITLE 职位	SIGNATURE 签名	DATE 日期	<b>Outgoing inspection report</b> 山化松磁报告 Template Number 模板 <b>Corp-F-QA-30</b>
QA	PeterLange	Quality vp	Lange	2024/1/17	


## Test Report

QR/QM-12

A/0

Grade	N35	Size	25*5 (10.4/5.5)	Date	2024/1/17	
Total Q'ty	2500	Samples	20PCS	Coating	NiCuNi	
Items	①	②	③	④	GAUSS	
	25	5	10.4	5.5		
Standard	+/-0.1	+/-0.1	+/-0.1	+/-0.1	N S	
Unit	mm	mm	mm	mm	Gs	
1	25.04	5.00	10.42	5.57	2860	2920
2	25.04	4.99	10.42	5.55	2900	2870
3	25.03	4.99	10.41	5.53	2890	2920
4	25.03	4.99	10.42	5.55	2880	3000
5	25.03	4.98	10.39	5.54	2910	2930
6	25.02	4.99	10.38	5.59	2920	2880
7	25.02	5.00	10.36	5.58	3020	2920
8	25.04	4.98	10.45	5.57	3010	3020
9	25.04	4.99	10.45	5.60	2920	2880
10	25.00	5.00	10.46	5.52	2960	2890
11	25.03	5.00	10.43	5.54	2950	2880
12	25.03	5.00	10.43	5.54	2920	2910
13	25.05	4.99	10.39	5.56	2870	2920
14	25.03	4.99	10.37	5.50	2920	3020
15	25.04	4.98	10.36	5.54	2910	2870
16	25.03	5.00	10.41	5.55	3000	2920
17	25.04	4.98	10.42	5.53	2930	2930
18	25.04	4.99	10.39	5.55	2970	2880
19	25.00	5.00	10.38	5.60	2990	2860
20	25.02	4.99	10.45	5.52	3010	2900
Max	25.05	5.00	10.46	5.60	3020	3020
Min	25.00	4.98	10.36	5.50	2860	2860
Avg	25.03	4.99	10.41	5.55	2940	2960
Decision	ok	ok	ok	ok	ok	ok





*S. Saleh*

Electronics  
Magnetic